

## Reactofix NF Dyes

### Black NF



#### SOLUBILITY

Plain .....	100
50 GPL Salt.....	50
100 GPL Urea.....	100

#### Light Fastness:

1/6.....	4-5
1/1.....	5

#### Washing Fastness:

Change in Shade .....	5
Staining on Adjacent Fabric .....	4-5

#### Rubbing Fastness:

Dry.....	3-4
Wet .....	3

(All information furnished is to the best of our knowledge but without warranty)

#### H2O2 Bleaching:

Change in Shade .....	5
Staining on Adjacent Fabric .....	4-5

#### Chlorinated Water:

Change in Shade .....	4-5
-----------------------	-----

#### Staining on Nylon

Change in Shade .....	5
-----------------------	---

#### Perspiration

Acidic

Acidic Change in Shade.....	5
Acidic Staining on Adjacent Fabric.....	5

Alkaline

Alkaline Change in Shade .....	5
Alkaline Staining on Adjacent Fabric.....	5