

Reactofix Supra Dyes

Black A

8.0% On Weight of Fabric



CHARACTERISTICS

- Deep black for exhaust dyeing with excellent washoff properties.
- Good build up, low staining of polyamide during dyeing.

TECHNICAL SPECIFICATIONS

General Properties

SUITABILITY

Exhaust	Suitable
Dyeing °C.....	
Silicate Pad Batch.....	Suitable
Printing	Suitable
Affinity	
Dischargeability	Medium Dischargeable

SOLUBILITY

with Water	
with 50 g/l Salt	
with 100 g/l UREA	

Note: The information contained herein, is provided in good faith but without warranty. It is the responsibility of the user to test our products as to their suitability for any application, use or processing. No Statement is intended or should be construed as a recommendation to infringe any patent and the responsibility to observe any such patent right, rests with the user.

(Without Warranty)

Fastness Properties

LIGHT ISO 105/B02

1/6 SD	As Black 5
--------------	---------------

By AATCC 16E (20AFU).....	3.0
---------------------------	-----

WASHING ISO 105/C0

Change in Shade	
Staining on Adjacent Fabric	

RUBBING ISO 105/X12

Dry	4-5
Wet	3

PERSPIRATION

NIKE TEST Acidic Light Fastness.....	3.0
NIKE TEST Alkaline Light Fastness	2.5
Post Mercerising Colour	4R
Change ISO/105/E04	

Post Mercerising Staining on	3-4
Cotton ISO/105/E04	

POST BLEACHING H2O2 ISO 105/N02

Colour Change.....	3
Staining on Cotton	4-5

Chlorinated Pool Water ISO 105/E03

Change in Shade	3-4
-----------------------	-----