




# Reactofix Supra Dyes

## Black HFGR

8.0% On Weight of Fabric



### CHARACTERISTICS

- Economical reddish black shade.
- Good build-up in exhaust dyeing.

### TECHNICAL SPECIFICATIONS

#### General Properties

##### SUITABILITY

Exhaust .....	Suitable
Dyeing °C	
Silicate Pad Batch .....	Not Suitable
Printing .....	Not Suitable
Affinity	
Dischargeability .....	Medium
	Dischargeable

##### SOLUBILITY

with Water	
with 50 g/l Salt .....	80
with 100 g/l UREA .....	100

Note: The information contained herein, is provided in good faith but without warranty. It is the responsibility of the user to test our products as to their suitability for any application, use or processing. No Statement is intended or should be construed as a recommendation to infringe any patent and the responsibility to observe any such patent right, rests with the user.

(Without Warranty)

#### Fastness Properties

##### LIGHT ISO 105/B02

1/6 SD .....	As
	Black 5

By AATCC 16E (20AFU).....	3.5
---------------------------	-----

##### WASHING ISO 105/C0

Change in Shade	
Staining on Adjacent Fabric	

##### RUBBING ISO 105/X12

Dry .....	4-5
Wet .....	2-3

##### PERSPIRATION ISO 105/E04

NIKE TEST Acidic Fastness.....	3.0
NIKE TEST Alkaline Light Fastness .....	3.5
Post Mercerising Colour	
Change ISO/105/E04.....	4R

Post Mercerising Staining on	
Change ISO/105/E04 .....	2-3

##### BLEACHING H2O2 ISO 105/N02

Change in Shade .....	3-4
Staining on Cotton .....	4-5

##### Chlorinated Pool Water ISO 105/E03

Change in Shade.....	4
----------------------	---