



Reactofix MESL Dyes

Blue MESL



TECHNICAL SPECIFICATIONS

General Properties

SUITABILITY

Exhaust	Suitable
Dyeing °C.....	60
Affinity.....	High

SOLUBILITY

Plain Water	50
with 50 g/l Salt	20
with 100 g/l UREA.....	100

Fastness Properties

LIGHT ISO 105/B02

1/1 SD	4-5
--------------	-----

WASHING ISO 105/C0

Change in Shade	4
Staining on Adjacent Fabric	4-5

PERSPIRATION ISO 105/E04

Acidic Change in Shade	4
Acidic Shading on Adjacent Fabric	4-5
Alkaline Change in Shade	4
Alkaline Shading on Adjacent Fabric.....	4-5

Note: The information contained herein, is provided in good faith but without warranty. It is the responsibility of the user to test our products as to their suitability for any application, use or processing. No Statement is intended or should be construed as a recommendation to infringe any patent and the responsibility to observe any such patent right, rests with the user.

(Without Warranty)

