



Reactofix SESL Dyes

Crimson SESL

2.0% On Mercerised Cotton



TECHNICAL SPECIFICATIONS

General Properties

SUITABILITY

Exhaust	Suitable
Dyeing °C.....	80
Affinity	High
Post Bleaching	Suitable

SOLUBILITY

with Water	100
with 50 g/l Salt	80
with 100 g/l UREA.....	100
Coverage of Cotton	Moderate

Note: The information contained herein, is provided in good faith but without warranty. It is the responsibility of the user to test our products as to their suitability for any application, use or processing. No Statement is intended or should be construed as a recommendation to infringe any patent and the responsibility to observe any such patent right, rests with the user.

(Without Warranty)

Fastness Properties

LIGHT ISO 105/B02

1/25 SD	3-4
1/1 SD	4

WASHING ISO 105/C0

Change in Shade	4-5
Staining on Adjacent Fabric	4-5

RUBBING ISO 105/X12

Dry.....	4-5
Wet.....	4

PERSPIRATION ISO 105/E04

Acidic Change in Shade.....	4-5
Acidic Staining on Adjacent Fabric	4-5
Alkaline Change in Shade	4
Alkaline Staining on Adjacent Fabric.....	4-5

BLEACHING H₂O₂ ISO 105/N02

Change in Shade	4
	Weaker, Bluer
Staining on Adjacent Fabric.....	4-5

Chlorinated Pool Water ISO 105/E03T

Change in Shade	4-5
	Bluer