

# Reactofix Supra Dyes

## Golden Yellow HERI

3.0% On Mercerised Cotton

### CHARACTERISTICS

- Good stability.
- Dischargeable.
- Non-flarring properties.
- Generally recommended for **trichromy combination**.
- Suitable for many applications including post mercerising, post bleaching.

### TECHNICAL SPECIFICATIONS

#### General Properties

##### SUITABILITY

Exhaust .....	Suitable
Dyeing °C.....	80
Affinity .....	High
Dischargeability .....	Dischargeable

##### SOLUBILITY

Plain Water .....	75
with 50 g/l Salt .....	30

Note: The information contained herein, is provided in good faith but without warranty. It is the responsibility of the user to test our products as to their suitability for any application, use or processing. No Statement is intended or should be construed as a recommendation to infringe any patent and the responsibility to observe any such patent right, rests with the user.

(Without Warranty)

#### Fastness Properties

##### LIGHT ISO 105/B02

1/1 SD.....	5
By AATCC 16E @2%.....	4

##### WASHING ISO 105/C0

Change in Shade .....	5
Staining on Adjacent Fabric .....	5

##### PERSPIRATION ISO 105/E04

Acidic Change in Shade .....	4-5
Alkaline Change in Shade .....	4-5

##### BLEACHING ISO 105/N02

NaOCI Change in Shade.....	2-3
H2O2 Change in Shade.....	4-5

##### Chlorinated Pool Water ISO 105/E03

Change in Shade.....	4-5
----------------------	-----

##### Sea Water ISO 105/E02

Change in Shade .....	4
Post Bleaching .....	Suitable