



Golden Yellow HRGB



Plain Water Solubility	100
50GPL Salt Solubility	60
Stability at 30°C	30 Min.
Exhaust Dyeing	Suitable
Cold-Pad-Batch	Suitable
Printing	Suitable

FASTNESS									
Light Fastness (Xenon ARC Lamp)			1/1	1/3	1/6	1/12	1/25		
			5-6	5	5	4-5	4-5		
Washing Fastness Multifiber Staining at 160°C	CS	CTA	CA	CO	PA	PES	PAN	CV	WOOL
	5	5	-	5	5	5	5	5	-
Perspiration (Acidic) (Alkaline)	5			5					5
	5			5					5
Water, Severe	5			5					5
Rubbing Fastness	DRY		WET		Dischargeability :			Dischargeable	
	4-5		4						
Cl₂ Water (20PPM Active Chlorine)			2-3						