

# Reactofix HE Dyes

## Green HE4B

3.0% On Mercerised Cotton

### CHARACTERISTICS

- Good solubility.
- Best recommended for bottle green shades.

### TECHNICAL SPECIFICATIONS

#### General Properties

##### SUITABILITY

Exhaust .....	Suitable
Dyeing °C.....	80
Affinity .....	High
Dischargeability .....	Medium Dischargeable

##### SOLUBILITY

Plain Water at .....	50
30°C	
with 50 g/l Salt .....	< 20

Note: The information contained herein, is provided in good faith but without warranty. It is the responsibility of the user to test our products as to their suitability for any application, use or processing. No Statement is intended or should be construed as a recommendation to infringe any patent and the responsibility to observe any such patent right, rests with the user.

(Without Warranty)

#### Fastness Properties

##### LIGHT ISO 105/B02

1/1 SD .....	5
--------------	---

##### WASHING ISO 105/C0

Change in Shade .....	4
Staining on Adjacent Fabric .....	3-4

##### PERSPIRATION ISO 105/E04

Acidic Change in Shade .....	3-4
Alkaline Change in Shade .....	4-5

##### BLEACHING H2O2 ISO 105/N02

NaOCl Change in Shade .....	1
H2O2 Staining on Adjacent Fabric .....	3-4

##### Chlorinated Pool Water ISO 105/E03

Change in Shade .....	4
-----------------------	---

##### Sea Water ISO 105/E02

Change in Shade .....	2-3
Post Bleaching .....	Less Suitable