

## Reactofix Supra Dyes

### N. Blue HRL

3.0% On Weight of Fabric



#### CHARACTERISTICS

- Product with high affinity.
- Very good built-up properties, suitable for dark blue and navy blue shades.
- For levelled dyeing, product is recommended in exhaust dyeing.

#### TECHNICAL SPECIFICATIONS

##### General Properties

###### SUITABILITY

Exhaust .....	Suitable
Dyeing °C.....	40-60
Silicate Pad Batch.....	Suitable
Printing.....	Not Suitable
Affinity .....	Very High
Dischargeability .....	Medium
	Dischargeable

###### SOLUBILITY

with Water .....	80
with 50 g/l Salt .....	15
with 100 g/l UREA.....	80

Note: The information contained herein, is provided in good faith but without warranty. It is the responsibility of the user to test our products as to their suitability for any application, use or processing. No Statement is intended or should be construed as a recommendation to infringe any patent and the responsibility to observe any such patent right, rests with the user.

(Without Warranty)

##### Fastness Properties

###### LIGHT ISO 105/B02

1/6 SD .....	3-4R
By AATCC 16E @ 0.1% .....	6

###### WASHING ISO 105/C0

Change in Shade .....	4
Staining on Adjacent Fabric .....	3

###### RUBBING ISO 105/X12

Dry.....	4
Wet .....	3

###### PERSPIRATION ISO 105/E04

Acidic Change in Shade .....	5
Acidic Staining on Adjacent Fabric .....	4
Alkaline Change in Shade .....	4-5
Alkaline Staining on Adjacent Fabric.....	4

###### BLEACHING H2O2 ISO 105/N02

Change in Shade .....	3
Staining on Adjacent Fabric .....	4

###### Chlorinated Pool Water ISO 105/E03

Change in Shade .....	2-3R
-----------------------	------