

Reactofix HE Dyes

Navy Blue HE2R

3.0% On Mercerised Cotton

CHARACTERISTICS

- A redder navy available.
- Generally used as per specific requirements.

TECHNICAL SPECIFICATIONS

General Properties

SUITABILITY

Exhaust	Suitable
Dyeing °C.....	80
Affinity	High
Dischargeability	Medium Dischargeable

SOLUBILITY

Plain Water at	> 100
30°C	
with 50 g/l Salt	> 100

Note: The information contained herein, is provided in good faith but without warranty. It is the responsibility of the user to test our products as to their suitability for any application, use or processing. No Statement is intended or should be construed as a recommendation to infringe any patent and the responsibility to observe any such patent right, rests with the user.

(Without Warranty)

Fastness Properties

LIGHT ISO 105/B02

1/1 SD	6
--------------	---

WASHING ISO 105/C0

Change in Shade	4
Staining on Adjacent Fabric	4

PERSPIRATION ISO 105/E04

Acidic Change in Shade	5
Alkaline Change in Shade	4-5

BLEACHING ISO 105/N02

NaOCl Change in Shade	2-3 Duller
-----------------------------	---------------

H2O2 Staining on Adjacent Fabric	4-5
--	-----

Chlorinated Pool Water ISO 105/E03

Change in Shade	3
-----------------------	---

Sea Water ISO 105/E02

Change in Shade	4-5
Post Bleaching	Less Suitable