

## Reactofix Supra Dyes

### Navy HRB H/C

8.0% On Weight of Fabric

#### CHARACTERISTICS

- Economical, dischargeable navy with exceptionally high colour value.
- Suitable for exhaust dyeing application.
- Excellent wet light fastness.

#### TECHNICAL SPECIFICATIONS

##### General Properties

###### SUITABILITY

Exhaust .....	Suitable
Dyeing °C	
Silicate Pad Batch .....	Not Suitable
Printing .....	Not Suitable
Affinity	
Dischargeability .....	Dischargeable

###### SOLUBILITY

with Water	
with 50 g/l Salt	
with 100 g/l UREA	

Note: The information contained herein, is provided in good faith but without warranty. It is the responsibility of the user to test our products as to their suitability for any application, use or processing. No Statement is intended or should be construed as a recommendation to infringe any patent and the responsibility to observe any such patent right, rests with the user.

(Without Warranty)

##### Fastness Properties

###### LIGHT ISO 105/B02

1/6 SD .....	As Navy 5
--------------	-----------

By AATCC 16E (20AFU).....4.0

###### WASHING ISO 105/C0

Change in Shade	
Staining on Adjacent Fabric	

###### RUBBING ISO 105/X12

Dry .....	4-5
Wet .....	2-3

###### PERSPIRATION

NIKE TEST Acidic Light Fastness.....	4.0
NIKE TEST Alkaline Light Fastness .....	3.5
Post Mercerising Colour .....	4-5R
Change ISO/105/E04	
Post Mercerising Staining on .....	3
Cotton ISO/105/E04	

###### POST BLEACHING ISO 105/N02

Colour Change.....	3-4
Staining on Cotton .....	4-5

###### Chlorinated Pool Water ISO 105/E03

Change in Shade .....	3-4
-----------------------	-----