

# Reactofix SESL Dyes

## Navy SESL

2.0% On Mercerised Cotton

### TECHNICAL SPECIFICATIONS

#### General Properties

##### SUITABILITY

Exhaust .....	Suitable
Dyeing °C.....	80
Affinity .....	High
Post Bleaching .....	Suitable

##### SOLUBILITY

with Water .....	100
with 50 g/l Salt .....	100
with 100 g/l UREA.....	100
Coverage of Cotton .....	Moderate

Note: The information contained herein, is provided in good faith but without warranty. It is the responsibility of the user to test our products as to their suitability for any application, use or processing. No Statement is intended or should be construed as a recommendation to infringe any patent and the responsibility to observe any such patent right, rests with the user.

(Without Warranty)

#### Fastness Properties

##### LIGHT ISO 105/B02

1/25 SD .....	3-4
1/1 SD .....	4

##### WASHING ISO 105/C0

Change in Shade .....	4-5
Staining on Adjacent Fabric .....	4-5

##### RUBBING ISO 105/X12

Dry.....	4-5
Wet.....	4-5

##### PERSPIRATION ISO 105/E04

Acidic Change in Shade.....	4
Acidic Staining on Adjacent Fabric .....	4-5
Alkaline Change in Shade .....	3-4
Alkaline Staining on Adjacent Fabric.....	4-5

##### BLEACHING H<sub>2</sub>O<sub>2</sub> ISO 105/N02

Change in Shade .....	3-4
	<b>Weaker</b>
Staining on Adjacent Fabric.....	5

##### Clorinated Pool Water ISO 105/E03T

Change in Shade .....	3-4
-----------------------	-----