



# Reactofix NE Dyes

## Reactofix Navy Blue NE-BL

2% On unmercerised cotton knitwear



### CHARACTERISTICS

- Redder blue recommended for darker shades.
- High affinity.

### TECHNICAL SPECIFICATIONS

#### General Properties

##### Solubility

|                          |    |
|--------------------------|----|
| Plain water at 80°C..... | 50 |
| Salt 80 g/l at 80°C..... | 25 |

##### LIGHT FASTNESS ISO 105/B02

|                          |     |
|--------------------------|-----|
| XENON Text : 1/1 SD..... | 4-5 |
|--------------------------|-----|

##### WASHING FASTNESS ISO 105/C04

|                                     |     |
|-------------------------------------|-----|
| Change in Shade.....                | 4-5 |
| Stain on adjacent white cotton..... | 4-5 |

##### PERSPIRATION ISO 105/E04

|               |     |
|---------------|-----|
| Acidic.....   | 4-5 |
| Alkaline..... | 4-5 |

#### Fastness Properties

##### RUBBING FASTNESS ISO 105/X12

|          |     |
|----------|-----|
| Dry..... | 4   |
| Wet..... | 2-3 |

##### CHLORINATED WATER ISO 105/E03

|                         |     |
|-------------------------|-----|
| 20 mg/ltr Chlorine..... | 4-5 |
|-------------------------|-----|

##### SEA WATER ISO 105/E02.....

|       |     |
|-------|-----|
| ..... | 4-5 |
|-------|-----|

##### NITROGEN OXIDE ISO 105/G02

|                 |     |
|-----------------|-----|
| Gas Fading..... | 4-5 |
|-----------------|-----|

##### STAINING

|          |     |
|----------|-----|
| Pet..... | 4-5 |
| Pa.....  | 4-5 |

Note: The information contained herein, is provided in good faith but without warranty. It is the responsibility of the user to test our products as to their suitability for any application, use or processing. No Statement is intended or should be construed as a recommendation to infringe any patent and the responsibility to observe any such patent right, rests with the user.

(Without Warranty)