



Reactosol Dyes

Reactosol Black CE

4% On untreated wool substrate



LIGHT

Light Fastness	5
----------------------	---

PERSPIRATION ISO 105/E04

ACIDIC

Change in Shade.....	5
Staining on Cotton.....	5
Staining on Wool.....	5

ALKALINE

Change in Shade	5
Staining on Cotton	5
Staining on Wool.....	5

ALKALINE MILLING ISO 105/E12

Change in Shade	5
Staining on Cotton.....	5
Staining on Wool.....	5

POTTING ISO 105/E09

Change in Shade.....	5
Staining on Cotton.....	5
Staining on Wool.....	5

Washing at 40°C ISO 105/C03

Change in Shade	5
Staining on Cotton.....	5
Staining on Wool.....	3-4

DECATISING ISO 105/E010

Change in Shade.....	5
----------------------	---

Note: The information contained herein, is provided in good faith but without warranty. It is the responsibility of the user to test our products as to their suitability for any application, use or processing. No Statement is intended or should be construed as a recommendation to infringe any patent a the responsibility to observe any such patent right, rests with the user.

(Without Warranty)