



Reactofix NF Dyes

Red 3BNF



SOLUBILITY

Plain	100
50 GPL Salt.....	100
100 GPL Urea.....	100

Light Fastness:

1/6.....	4-5
1/1.....	5

Washing Fastness:

Change in Shade	4
Staining on Adjacent Fabric	4-5

Rubbing Fastness:

Dry	4-5
Wet	3-4

H2O2 Bleaching:

Change in Shade.....	4
Staining on Adjacent Fabric	4-5

Chlorinated Water:

Change in Shade	4
-----------------------	---

Staining on Nylon

Change in Shade	4
-----------------------	---

Perspiration

Acidic	
Acidic Change in Shade.....	4
Acidic Staining on Adjacent Fabric	4
Alkaline	
Alkaline Change in Shade	4-5
Alkaline Staining on Adjacent Fabric.....	4

(All information furnished is to the best of our knowledge but without warranty)