

# Reactofix Supra Dyes

## Red HBBLC

2.0% On Weight of Fabric

### CHARACTERISTICS

- High Affinity, high tinctorial Red.
- The only Dischargeable Red suitable for exhaust dyeing.
- Good Washing Fastness.
- Stable to peroxide bleaching.
- Suitable for exhaust, silicate pad batch and printing process.

### TECHNICAL SPECIFICATIONS

#### General Properties

##### SUITABILITY

Exhaust .....	Suitable
Dyeing °C.....	40-60
Silicate Pad Batch.....	Suitable
Printing.....	Suitable
Affinity .....	High
Dischargeability .....	Dischargeable

##### SOLUBILITY

with Water .....	50
with 50 g/l Salt .....	20
with 100 g/l UREA.....	100

Note: The information contained herein, is provided in good faith but without warranty. It is the responsibility of the user to test our products as to their suitability for any application, use or processing. No Statement is intended or should be construed as a recommendation to infringe any patent and the responsibility to observe any such patent right, rests with the user.

(Without Warranty)

#### Fastness Properties

##### LIGHT ISO 105/B02

1/6 SD .....	4-5
1/1 SD .....	5

##### WASHING ISO 105/C0

Change in Shade .....	4-5
Staining on Adjacent Fabric .....	4-5

##### RUBBING ISO 105/X12

Dry.....	5
Wet .....	3-4

##### PERSPIRATION ISO 105/E04

Acidic Change in Shade .....	4-5
Acidic Staining on Adjacent Fabric .....	5
Alkaline Change in Shade .....	4-5
Alkaline Staining on Adjacent Fabric.....	4-5

##### BLEACHING H2O2 ISO 105/N02

Change in Shade .....	4-5
Staining on Adjacent Fabric .....	5

##### Chlorinated Pool Water ISO 105/E03

Change in Shade .....	2
-----------------------	---