

Reactofix HE Dyes

Red HE3B

3.0% On Mercerised Cotton



CHARACTERISTICS

- Good solubility.
- Yellowish red shade.
- Recommended in **trichromy** for light to pale shades.

TECHNICAL SPECIFICATIONS

General Properties

SUITABILITY

Exhaust	Suitable
Dyeing °C.....	80
Affinity.....	High
Dischargeability.....	Not Dischargeable

SOLUBILITY

Plain Water at 30°C.....	30
with 50 g/l Salt	< 10

Note: The information contained herein, is provided in good faith but without warranty. It is the responsibility of the user to test our products as to their suitability for any application, use or processing. No Statement is intended or should be construed as a recommendation to infringe any patent and the responsibility to observe any such patent right, rests with the user.

(Without Warranty)

Fastness Properties

LIGHT ISO 105/B02

1/1 SD	5
--------------	---

WASHING ISO 105/C0

Change in Shade	5
Staining on Adjacent Fabric	4-5

PERSPIRATION ISO 105/E04

Acidic Change in Shade.....	4-5
Alkaline Change in Shade.....	4-5

BLEACHING ISO 105/N02

NaOCI Change in Shade.....	1-2
H2O2 Change in Shade	4

Chlorinated Pool Water ISO 105/E03

Change in Shade.....	4
----------------------	---

Sea Water ISO 105/E02

Change in Shade	4
Post Bleaching.....	Suitable