

Reactofix HE Dyes

Red HE8B

3.0% On Mercerised Cotton

CHARACTERISTICS

- Good solubility.
- High tinctorial value.
- Bluish red shade.

TECHNICAL SPECIFICATIONS

General Properties

SUITABILITY

Exhaust	Suitable
Dyeing °C.....	80
Affinity.....	High
Dischargeability.....	Not Dischargeable

SOLUBILITY

Plain Water at 30°C.....	80
with 50 g/l Salt	> 60

Note: The information contained herein, is provided in good faith but without warranty. It is the responsibility of the user to test our products as to their suitability for any application, use or processing. No Statement is intended or should be construed as a recommendation to infringe any patent and the responsibility to observe any such patent right, rests with the user.

(Without Warranty)

Fastness Properties

LIGHT ISO 105/B02

1/1 SD	4-5
By AATCC 16E @ 2%.....	2.5

WASHING ISO 105/C0

Change in Shade	4-5
Staining on Adjacent Fabric	2-3

PERSPIRATION ISO 105/E04

Acidic Change in Shade.....	4
Alkaline Change in Shade.....	4-5

BLEACHING ISO 105/N02

NaOCI Change in Shade.....	3-4
	Bluer
H2O2 Change in Shade	4-5

Chlorinated Pool Water ISO 105/E03

Change in Shade	4-5
	Bluer

Sea Water ISO 105/E02

Change in Shade.....	4
Post Bleaching.....	Less Suitable