

Reactofix ME Dyes

Red ME4BL 150%

2.0% On Weight of Fabric

CHARACTERISTICS

- Very high affinity dyestuff. Suitable for exhaust dyeing.
- Best resistance to chlorine among existing bright reactive reds.
- Good shading dye and has wide fixation temperature range.
- Insensitive to variation in liquor ratio during exhaust dyeing.
- Recommended in **trichromy** for medium to dark shades.

TECHNICAL SPECIFICATIONS

General Properties

SUITABILITY

Exhaust	Suitable
Dyeing °C.....	60
Cold Pad Batch.....	Suitable
Silicate	
Affinity	High
Dischargeability	Not Dischargeable

SOLUBILITY

Plain Water	100
with 50 g/l Salt	100
with 100 g/l UREA	100

Note: The information contained herein, is provided in good faith but without warranty. It is the responsibility of the user to test our products as to their suitability for any application, use or processing. No Statement is intended or should be construed as a recommendation to infringe any patent and the responsibility to observe any such patent right, rests with the user.

(Without Warranty)

Fastness Properties

LIGHT ISO 105/B02

1/6 SD	4-5
--------------	-----

WASHING ISO 105/C0

Change in Shade	4
Staining on Adjacent Fabric	4-5

PERSPIRATION ISO 105/E04

Acidic Change in Shade	4-5
Acidic Staining on Adjacent Fabric	4
Alkaline Change in Shade	4-5
Alkaline Staining on Adjacent Fabric.....	4

BLEACHING H2O2 ISO 105/N02

NaOCl Change in Shade	3
NaOCl Staining on Adjacent Fabric	3-4
H2O2 Change in Shade.....	4
H2O2 Staining on Adjacent Fabric	4-5

Chlorinated Pool Water ISO 105/E03

Change in Shade	4
-----------------------	---

Sea Water ISO 105/E02

Change in Shade	4-5
Staining on Adjacent Fabric	4
Staining on Nylon	4